



# SPRAY P 962 1K ISOLATOR PRIMER

Technical Data Sheet No 830



VOC compliant with the regulations.

One component air drying system

Dries quickly

P 962 1K ISOLATOR PRIMER prevents lifting and bleeding of existing old paint films, sensitive to strong solvents.

## General Technical Description

2 passes

## Surface

All metallic and wooden surfaces

Adhesion to any coated surface

## Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL/ BODY 771 ANTISIL FAST

Use P 400 for wet sanding, re-clean the surface and dry thoroughly

Use P 180 for sanding on applications direct to metals



Make sure you always use appropriate face protection and good ventilation

**Product Application:** >>> Apply on a light sanded surface using wet / dry P180 grit paper. Apply 2 light coats at an approximately distance of 20 - 25cm. No sanding after application.



Shake well before using

**Flash Point:**  
-97°C

### Remarks:

- Always try to use the product in accordance with the specifications provided.
- It can be used by countries that do not adopt the VOC legislation as well.
- Shake thoroughly before use.

### Storage shelf life:

- Store in a cool place (+5°C - +25°C) and use within 12 months for best results. Guaranteed shelf life of 24 months in unused original containers.
- Do not overload



2 coats approximately 20 - 25microns

**Specific Gravity:**  
0,95 g/cm<sup>3</sup>

**Solid Content (No thinner):**  
35% Weight

### VOC (2004/42/EC)

This product is an aerosol product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 585g/L. 2004/42/II(b)(e)(840)585

• Shake for 1-2 mins after agitator ball has started to rattle. After preparing the area to be painted ensure it to be free from dirt, wax, oil etc. Test on a similar surface using a back and forth action.

• Spray at a distance of 25 cm thinly applied coats build up at 3-5 minutes intervals will achieve best results.

• Optimum operating temperature range 10-25°C.



Dust free 10 - 15min at 23°C



Full hardness within 1 hour

**Theoretical Coverage:**  
-



Overcoat with primer / surfacer

**Cleaning of equipment:**  
-

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

Issue 2/2016, August 2016